

PALACE-LUX



189



101



124



170



114



192



189



144



179



116



BEST IN PURE WOOL

SINCE 1982

PALACE LUX



WIDTH 400
BREITE
LARGEUR

THERMAL CONDUCTIVITY $m^2 / K/W$ 0.17
WÄRMEDURCHLASSWIDERSTAND $m^2 / K/W$
RESISTANCE THERMIQUE $m^2 / K/W$

PILE FIBRE COMPOSITION 100% Pure New Zealand Wool
MATERIAL DER NUTZSCHICHT 100% reine Neuseeland Schurwolle
COMPOSITION DU VELOURS 100% Pure laine vierge de Nouvelle Zélande

LUXURY CLASS LC 5
LUXUSKLASSE
CLASSE DE LUX

YARN SPECIFICATION 3-ply yarn, hank dyed
GARNE-SPEZIFIKATION 3-fach Garn, stranggefärbt
SPÉCIFICATIONS DU FIL Fil 3 bouts, teint sur écheveaux

FLOORSYMBOLS
TEPPICHBODENSYMBOL
SYMBOLES DE SOL

MASS OF PILE g/m^2 2.000
POLEINSATZGEWICHT g/m^2
MASSE TOTALE g/m^2



TOTAL MASS g/m^2 2.930
GESAMTGEWICHT g/m^2
MASSE TOTALE g/m^2



NUMBER OF TUFTS / m^2 39.401
NOPPENZAHL / m^2
NOMBRE DE TOUFFES / m^2



TOTAL THICKNESS in mm 11.0
GESAMTDICKE in mm
ÉPAISSEUR TOTALE in mm

JAMES
THE FINISHING TOUCH



BEST IN PURE WOOL

SINCE 1982